

MINFILE Number:		Name:		Status:	
Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments	
MAIN 1991	N	Assay/analysis Drill Core	Copper Gold 0.312 % 0.240 g/t	over 42.0 metres in hole RO-01-91 Peatfield, G.R. (2006-09-20): Technical Report on the ROK Copper-Gold Mineral Property	
SOUTH 1991	N	Assay/analysis Drill Core	Copper Gold 0.180 % 0.240 g/t	over 6.0 metres in hole RO-04-91 Peatfield, G.R. (2006-09-20): Technical Report on the ROK Copper-Gold Mineral Property	
SOUTH 1990	N	Assay/analysis Chip	Copper Gold 0.325 % 0.206 g/t	sampling of trenches on the South zone yielded up to 0.325 per cent copper and 0.206 gram per tonne gold over 27.0 metres in trench no. 13 Peatfield, G.R. (2006-09-20): Technical Report on the ROK Copper-Gold Mineral Property	
MAIN 1990	N	Assay/analysis Chip	Copper Gold 0.449 % 0.377 g/t	sampling of trenches on the Main zone yielded values of up to 0.449 and 0.530 per cent copper with 0.377 and 0.617 gram per tonne gold over 114 and 36.0 metres from trenches no. 1 and 2a, respectively Peatfield, G.R. (2006-09-20): Technical Report on the ROK Copper-Gold Mineral Property	
MAIN 1990	N	Assay/analysis Drill Core	Copper Gold 1.32 % 1.540 g/t	over 38.37 metres in hole 90-R03 Peatfield, G.R. (2006-09-20): Technical Report on the ROK Copper-Gold Mineral Property	
DRILLHOLE 1982	N	Assay/analysis Drill Core	Gold Copper 0.0400 g/t 1.0700 %	Grades averaged over 15 metre intercept width. Assessment Report 17316.	