

MINFILE Number: 104I 016	Name: CM	Status: Prospect
---------------------------------	-----------------	-------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE		Copper	4.54 %	Sample (64088) of bleached, strongly clay-altered breccia containing 5 per cent malachite and 2 per cent chalcocite. Assessment Report 22042.
1991	Assay/analysis Grab	Silver	60.3 g/t	
DRILLHOLE		Silver	8.5700 g/t	From a 6.1-metre drill interval. Assessment Report 3237.
1971	Assay/analysis Drill Core	Copper	0.3900 %	