

<b>MINFILE Number:</b> 104J 013	<b>Name:</b> HU	<b>Status:</b> Prospect
---------------------------------	-----------------	-------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE 2012      N	Assay/analysis Grab	Copper Gold	2.02 % 0.708 g/t	a grab sample (966982) of potassium feldspar rich syenite hosting fine disseminated pyrite Bowen, B.K. (2013-04-30): Technical Report on the Galaxie Project
SAMPLE 2007      N	Assay/analysis Rock	Copper Gold	0.30 % 0.06 g/t	An average from a 50 metre wide zone of structurally controlled quartz and carbonate vein mineralization (samples 147703-147705 and 149515-149519). Assessment Report 29434.
SAMPLE 1991      N	Assay/analysis Grab	Gold Copper	1.3000 g/t 1.1400 %	Highest copper value from an area of intense fracturing; highest gold result from fault gouge. Assessment Report 21707, page 12.