

<b>MINFILE Number:</b>	104J 035	<b>Name:</b>	STAR	<b>Status:</b>	Prospect
------------------------	----------	--------------	------	----------------	----------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
2007	N	Assay/analysis Drill Core	Gold	0.19 g/t	229.17 metres in hole CC2007-04 Caron, L. (2013-07-16): National Instrument 43-101 Technical Report on the Sheslay Property
			Copper	0.41 %	
2007	N	Assay/analysis Drill Core	Copper	0.35 %	over 334.67 metres in hole CC2007-01 Caron, L. (2013-07-16): National Instrument 43-101 Technical Report on the Sheslay Property
			Gold	0.17 g/t	
2005	N	Assay/analysis Drill Core	Copper	0.44 %	over 142.08 metres in hole CC2005-09 Caron, L. (2013-07-16): National Instrument 43-101 Technical Report on the Sheslay Property
			Gold	0.25 g/t	
2004	N	Assay/analysis Chip	Copper	0.37 %	trenching over an area of approximately 300 by 400 metres yielded up to 0.37 per cent copper and 0.23 gram per tonne gold over 270 metres, including 0.51 per cent copper and 0.25 gram per tonne gold over 138 metres from the Upper Main trench Caron, L. (2013-07-16): National Instrument 43-101 Technical Report on the Sheslay Property
			Gold	0.23 g/t	
2004	N	Assay/analysis Drill Core	Copper	0.80 %	An average over 52.3 metres. Exploration and Mining in British Columbia 2004, page 27.
			Gold	0.73 g/t	
2003	N	Assay/analysis Chip	Copper	0.35 %	sampling of trenches yielded up to 0.35 per cent copper and 0.32 gram per tonne gold over 40 metres in trench CC-TR-2003-1 Caron, L. (2013-07-16): National Instrument 43-101 Technical Report on the Sheslay Property
			Gold	0.32 g/t	
1977	N	Assay/analysis Grab	Copper	0.4000 %	Widespread areas with this average copper content. Geology in British Columbia 1977-1981, page 178.
1977	N	Assay/analysis Chip	Copper	0.44 %	trenching yielded 0.33 and 0.44 per cent copper over 70 and 179 metres in trenches TR1W and TR2W, respectively Caron, L. (2013-07-16): National Instrument 43-101 Technical Report on the Sheslay Property