MINFILE Number: 104K 028 **Name:** MAD **Status:** Showing

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE 2004	N	Assay/analysis Grab	Gold	1.31 g/t	a grab sample (276527) of weakly silicified sandstone with 1 to 3 per cent pyrite Baker, D. (2010-10-28): 2010 Technical Report on the Thorn Property
VEIN 2004	N	Assay/analysis Chip	Gold Silver Lead Zinc	13.35 g/t 324 g/t 0.522 % 0.340 %	a 0.20 metre chip sample (276528) of chalcedonic vein breccia, while other chip samples of chalcedonic vein breccia, varying from 0.1 to 0.5 metre in length, yielded values of up to 2.53 grams per tonne gold, 1255 grams per tonne silver, 0.146 per cent copper, 1.09 per cent lead and 5.07 per cent zinc Baker, D. (2010-10-28): 2010 Technical Report on the Thorn Property
SAMPLE 1986	N	Assay/analysis Rock	Silver Arsenic Gold Copper Lead Zinc	13.2000 g/t 0.0040 % 0.0400 g/t 0.0230 % 1.3200 % 0.0410 %	Sample #72420 from silicified zone. Assessment Report 15477.