MINFILE Number: 104K 031 **Name:** THORN **Status:** Prospect

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
VEIN 2004 N	Assay/analysis Drill Core	Gold Silver Copper Lead Zinc	5.27 g/t 54.0 g/t 0.16 % 0.67 % 1.69 %	5.27 and 1.59 grams per tonne gold, 54.0 and 83.9 grams per tonne silver, 0.16 and 1.32 per cent copper, 0.67 and 0.02 per cent lead with 1.69 and 0.03 per cent zinc over 1.01 and 3.95 metres, respectively, in hole 04-31 from the Tamdhu vein. Baker, D. (2010-10-28): 2010 Technical Report on the Thorn Property
VEIN 2004 N	Assay/analysis Drill Core	Gold Silver Copper Zinc	1.11 g/t 368.9 g/t 2.96 % 0.61 %	1.70 and 1.11 grams per tonne gold, 89.6 and 368.9 grams per tonne silver, 1.40 and 2.96 per cent copper and 0.14 and 0.61 per cent zinc over 0.62 and 0.37 metres, respectively, in hole 04-30 on the MP vein. Baker, D. (2010-10-28): 2010 Technical Report on the Thorn Property
VEIN 2002 N	Assay/analysis Drill Core	Gold Silver Copper	3.10 g/t 454 g/t 3.65 %	Over 1.65 metres in hole 02-13 on the Tamdhu vein. Baker, D. (2010-10-28): 2010 Technical Report on the Thorn Property
MAIN TARGET 1987 N	Assay/analysis Drill Core	Silver Gold Copper	152.6000 g/t 2.0000 g/t 3.7800 %	2.58 metre sample. Assessment Report 15897.
MAIN TARGET 1986 N	Assay/analysis Drill Core	Gold Silver Copper	1.013 g/t 22.2 g/t 0.16 %	Drilling on the main target of the B zone over 41.50 metres (approximately 29.4 metres true width), including 7.8 metres (approximately 5.5 metres true width) grading 3.619 grams per tonne gold, 44.3 grams per tonne silver and 0.18 per cent copper. Baker, D. (2010-10-28): 2010 Technical Report on the Thorn Property