

<b>MINFILE Number:</b> 104N 078	<b>Name:</b> BOOT	<b>Status:</b> Prospect
---------------------------------	-------------------	-------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE		Silver	68.0000 g/t	Fluorine assays 0.345 per cent.
	Assay/analysis	Copper	1.5600 %	Assessment Report 6127.
1976	Grab	Lead	0.0920 %	
N		Tin	0.2040 %	
		Tungsten	0.0720 %	
		Zinc	0.4560 %	