

MINFILE Number:	104P 003	Name:	LAMB MOUNTAIN	Status:	Prospect
------------------------	----------	--------------	---------------	----------------	----------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
DRILLHOLE			Tungsten	0.57 %	Drilling yielded up to 0.57 per cent tungsten tri-oxide over 4.7 metres in hole 9W 2 and 0.36 per cent tungsten tri-oxide over 24.9 metres in hole 9W 4, while drill hole 9W 7 intersected 8.7 metres of actinolite rich skarn hosting molybdenite but no assays were reported for this section. Assessment Report 7965
1979	N	Assay/analysis Drill Core			
TRENCH			Tungsten	0.70 %	Samples of rubble from trench No. 1 (Ridge Crest) over 10 metres, value is reported as tungsten tri-oxide. Assessment Report 7242
1978	N	Assay/analysis Chip			
TRENCH			Tungsten	0.72 %	A grab sample from trench No. 4, located approximately 480 metres south and 190 metres lower than trench No. 1. Value is reported as tungsten tri-oxide. Assessment Report 7242
1978	N	Assay/analysis Grab			
TRENCHES			Molybdenum	1.65 %	In 1960 and 1961, sampling of trenches nos. 1, 2 (North Channel), 2 (South Channel) and 4 is reported to have yielded an average of 0.54, 1.05, 0.96 and 1.65 per cent molybdenite over 3.3, 3.6, 2.1 and 4.0 metres, respectively Assessment Report 7965
1961	N	Assay/analysis Chip			
DRILLHOLE			Molybdenum	0.83 %	Diamond drilling is reported to have yielded up to 0.49 and 0.83 per cent molybdenite over 17.3 and 12.8 metres in hole 4 and 5, respectively Assessment Report 7965
1961	N	Assay/analysis Drill Core			