

<b>MINFILE Number:</b>	104P 027	<b>Name:</b>	KIRK	<b>Status:</b>	Prospect
------------------------	----------	--------------	------	----------------	----------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
A	1999	N Assay/analysis Rock	Copper	0.85 %	A rock sample (648-TC-04) of massive pyrite and sphalerite in calcite gangue from the No. 1 or 2 zone. Assessment Report 26150
			Lead	2.23 %	
			Zinc	17.55 %	
			Silver	95.0 g/t	
B	1978	N Assay/analysis Chip	Copper	2.76 %	A chip sample on the B (No. 4) zone over 3.0 metres. Assessment Report 7113
			Zinc	1.48 %	
			Silver	49.4 g/t	
A	1978	N Assay/analysis Chip	Silver	99.4100 g/t	Chip sample over 3 metres of the A (1 and 2) zone. Assessment Report 7113.
			Copper	1.0100 %	
			Lead	0.3900 %	
			Zinc	1.1000 %	
1	1969	N Assay/analysis Chip	Silver	29.3 g/t	Chip samples, taken at 0.3 metre intervals, over 39 metres of the No.1 zone. Individual samples (36793 through 36795) yielded up to 0.9 gram per tonne gold, 144 grams per tonne silver, 8.90 per cent lead, 16.50 per cent lead and 4.90 per cent copper. Assessment Report 2765
			Lead	0.69 %	
			Zinc	2.39 %	
			Copper	0.18 %	