

<b>MINFILE Number:</b> 104P 164	<b>Name:</b> HILL 1818	<b>Status:</b> Showing
---------------------------------	------------------------	------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE 2003	N Assay/analysis Grab	Lead Zinc Silver	2.3 % 3.8 % 212 g/t	Samples of oxidized surface exposures yielded up to 2.3 per cent lead, 3.8 per cent zinc, 212 grams per tonne silver and 0.2 gram per tonne gold. Assessment Report 27337.
SAMPLE 2002	N Assay/analysis Grab	Lead Zinc Silver	0.6 % 1.0 % 82 g/t	Sampling of the Hill 1818 zone. Assessment Report 27203.