

|                                  |                              |                        |
|----------------------------------|------------------------------|------------------------|
| <b>MINFILE Number:</b> 082FSW034 | <b>Name:</b> TUNGSTEN KING 1 | <b>Status:</b> Showing |
|----------------------------------|------------------------------|------------------------|

| Ore Zone/<br>Year/Report On | Tonnage/<br>Category        | Commodity              | Grade                         | Reference/<br>Comments   |
|-----------------------------|-----------------------------|------------------------|-------------------------------|--|
| SAMPLE<br>1996              | N<br>Assay/analysis<br>Rock | Zinc<br>Silver         | 16.33 %<br>9.2 g/t            | a sample (TK-10) of banded sphalerite in dolomite<br>Assessment Report 24910                                     |
| SKARN<br>1996               | N<br>Assay/analysis<br>Rock | Silver                 | 1.7 g/t                       | a sample (TK-12) of siliceous skarn in quartzites with<br>pyrrhotite mineralization<br>Assessment Report 24910   |
| SKARN<br>1996               | N<br>Assay/analysis<br>Rock | Lead<br>Zinc<br>Silver | 4.43 %<br>2.40 %<br>133.9 g/t | four samples (TK-104, -105, -13 and -15) of the<br>mineralized skarny limestone bands<br>Assessment Report 24910 |
| SAMPLE<br>1956              | N<br>Assay/analysis<br>Chip | Silver<br>Lead<br>Zinc | 6.86 g/t<br>0.27 %<br>8.4 %   | a sample (7085M) over 68 centimetres<br>Bulletin 41, page 153  |