

MINFILE Number: 092GNW063	Name: JR	Status: Prospect
----------------------------------	-----------------	-------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
MAIN 2023	N Assay/analysis Drill Core	Gold	1.40 g/t	diamond drilling yielded intercepts of up to 1.40 grams per tonne gold over 0.74 metre in hole DA2023-JR-01 Assessment Report 42138
MAIN 2022	N Assay/analysis Rock	Gold	2.02 g/t	a rock sample (DA2022-S0002) from a new roadcut in the JR zone exposing a granodiorite in contact with an andesite hosting narrow, 3- to 5-centimetre wide, quartz veins with pyrite and marcasite. This area is located approximately 50 metres north of the main JR zone. Assessment Report 40899
MAIN 2021	N Assay/analysis Rock	Gold	5.74 g/t	a rock sample (JR-2) of quartz vein material from the JR zone Assessment Report 39676
MAIN 2019	N Assay/analysis Rock	Gold	14.9 g/t	four rock samples (DA19-JR-1 to -3 and DA19-S0008) from the JR zone yielded from 1.5 to 14.9 grams per tonne gold Assessment Report 39205
3 2018	N Assay/analysis Rock	Gold Silver	9.30 g/t 21.0 g/t	two samples (DA18-3V-S1 and -S2) from the 3V zone yielded 9.30 and 3.95 grams per tonne gold with 21.0 and 12.0 grams per tonne silver, respectively Assessment Report 39205
D 2015	N Assay/analysis Grab	Gold Silver	8.68 g/t 29.0 g/t	sample (2015-004) comprising a collection of rocks from a 1.5 metre diameter area of granitic rocks from the DF vein area Assessment Report 35627
D 2012	N Assay/analysis Chip	Silver Gold	64.9 g/t 66.55 g/t	two chip samples (2012-022 and 2012-028) from the DF vein area yielded 64.9 and 42.1 grams per tonne silver with 66.55 and 48.25 grams per tonne gold over 0.2 and 1.0 metre, respectively Assessment Report 33765
3 2011	N Assay/analysis Chip	Gold Silver	9.58 g/t 20 g/t	a chip sample (87646) from the 3V zone yielded 9.58 grams per tonne gold and 20 grams per tonne silver over 1.0 metre Assessment Report 32343
D 2010	N Assay/analysis Grab	Gold Silver	58.69 g/t 79 g/t	three samples (no. 1 to 3) of mineralized quartz veins from the DF zone yielded from 3.01 to 58.69 grams per tonne gold and 13 to 79 grams per tonne silver Assessment Report 31885

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
3 2010	N Assay/analysis Grab	Gold Silver	2.44 g/t 7 g/t	a float sample (no. 4) mineralized quartz from historical trenches on the 3V zone Assessment Report 31885
2 2010	N Assay/analysis Rock	Gold Silver	0.70 g/t 8 g/t	a sample (no. 8) from the T vein Assessment Report 31885
TRENCH 2010	N Assay/analysis Grab	Gold Silver	48.35 g/t 49 g/t	two float samples (no. 5 and 6) of mineralized quartz vein material from the historical Trench no. 2 area yielded 48.35 and 4.95 grams per tonne gold with 49 and 10 grams per tonne silver, and a sample (No. 7) of silicified granodiorite hosting minor sulphides yielded 1.00 gram per tonne gold and 7 grams per tonne silver Assessment Report 31885
3 1993	N Assay/analysis Grab	Gold Silver	37.4 g/t 60.5 g/t	average of two samples (no. 1 and 2) from the 3V zone Assessment Report 23354
MAIN 1993	N Assay/analysis Grab	Gold Silver	7.1 g/t 5.8 g/t	a sample (no. 5) from the JR vein Assessment Report 23354
MAIN 1988	N Assay/analysis Chip	Gold	1.60 g/t	two chip samples (WH-011 and WH-012) from mineralized veins on the JR zone yielded values of 1.08 and 1.60 grams per tonne gold over 0.45 and 0.50 metre, respectively Assessment Report 17941
D 1988	N Assay/analysis Grab	Silver Gold	170.2 g/t 90.72 g/t	a grab sample (WH-018) from the DF zone Assessment Report 17941
3 1988	N Assay/analysis Grab	Silver Gold	77.2 g/t 26.25 g/t	six samples (WH-003 through WH-008) of vein material from the 3V zone yielded values from 0.7 to 77.2 grams per tonne silver and 0.47 to 26.25 grams per tonne gold Assessment Report 17941
3 1985	N Assay/analysis Grab	Gold Silver	183.2 g/t 347.6 g/t	samples from the zoned yielded values up to 183.2 grams per tonne gold and 347.6 grams per tonne silver Assessment Report 14736
3 1985	N Assay/analysis Drill Core	Gold Silver	2.3 g/t 5.1 g/t	drilling on the 3V zone yielded intercepts of up to 2.3 grams per tonne gold with 5.1 grams per tonne silver over 0.6 metre in hole 3V-6 Assessment Report 14736
D 1985	N Assay/analysis Chip	Gold Silver	49.96 g/t 83.0 g/t	a chip sample taken across 2 metres on DF zone Assessment Report 14736

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
D		Gold	3.20 g/t	drilling on DF zone, over 0.3 metre in hole DF DDH-2 Assessment Report 14736
1985	N	Assay/analysis Drill Core		
MAIN		Silver	21.4000 g/t	diamond drilling intersected a section of massive marcasite with electrum in quartz averaging 31.3 grams per tonne gold and 21.4 grams per tonne silver over a core length of 2.7 metres in hole JR DDH-9 on the JR zone. Assessment Report 14736.
1985	N	Assay/analysis Drill Core	Gold 31.3000 g/t	
MAIN		Gold	6.86 g/t	surface samples yielded values of up to 6.86 grams per tonne gold and 6.72 grams per tonne silver Assessment Report 14736
1985	N	Assay/analysis Grab	Silver 6.72 g/t	
TRENCH		Gold	7.5 g/t	a sample from trench no. 2 Assessment Report 14736
1985	N	Assay/analysis Grab	Silver 11.6 g/t	
2		Gold	2.3 g/t	sampling of the T and PC veins yielded 1.7 and 2.3 grams per tonne gold, respectively (Samples RT and RPC) Assessment Report 11129
1982	N	Assay/analysis Grab		