

<b>MINFILE Number:</b> 092HNE084	<b>Name:</b> PAYCINCI	<b>Status:</b> Developed Prospect
----------------------------------	-----------------------	-----------------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
PAYCINCI 1998 Y	1,800 kt Inferred	Copper	1.0000 %	Reserve estimate. Tom Schroeter, 1998.
PIT 1995 N	Assay/analysis Grab	Copper	2.38 %	A sample (618-K) from the shaft or pit exposing a 2-metre wide shear zone with malachite staining. Assessment Report 24019
TRENCHES 1995 N	Assay/analysis Chip	Copper	2.99 %	Chip sampling (618-I, -J, -L, -M and -N) of trenches located near an infilled shaft or test pit yielded from 0.76 per cent copper over 15 metres to 2.99 per cent copper over 4 metres. Assessment Report 24019
TRENCHES 1992 N	Assay/analysis Chip	Copper	1.25 %	Chip sampling of the Cincinatti and Sherwin trenches, located approximately 100 and 300 metres to the south of the adit, respectively, yielded 1.25 and 0.29 per cent copper over 10 and 25 metres, respectively. Assessment Report 22382
ADIT 1992 N	Assay/analysis Rock	Copper	0.198 %	Sample (92022) from the Cincinatti adit area. Assessment Report 22382
TRENCHES 1985 N	Assay/analysis Rock	Copper Silver	2.4 % 5.7 g/t	Six rock samples (2051 to 2056) from historic trenches, extending for approximately 500 metres along a north-south strike, analysed 1.1 to 2.4 per cent copper, 0.005 to 0.010 gram per tonne gold and 1.3 to 5.7 grams per tonne silver. Assessment Report 14108, Figure 5
CINCINNATTI 1979 Y	54 kt Indicated	Copper	0.8760 %	Drill indicated reserves based on 2 drillholes. Assessment Report 7654.