

|                                  |                                |                        |
|----------------------------------|--------------------------------|------------------------|
| <b>MINFILE Number:</b> 092HNE088 | <b>Name:</b> PORTLAND (L.1124) | <b>Status:</b> Showing |
|----------------------------------|--------------------------------|------------------------|

| Ore Zone/<br>Year/Report On |   | Tonnage/<br>Category   | Commodity        | Grade              | Reference/<br>Comments  |
|-----------------------------|---|------------------------|------------------|--------------------|---|
| DUMP                        |   |                        | Copper           | 0.170 %            | Shaft dump sample K-06.<br>Assessment Report 28782  |
| 2006                        | N | Assay/analysis<br>Grab |                  |                    |   |
| DUMP                        |   |                        | Copper<br>Silver | 1.125 %<br>5.0 g/t | Four composite grab samples (28347 through 28350) of waste and ore dump material from the Portland shaft yielded from 0.311 to 1.125 per cent copper with 1.6 to 5.0 grams per tonne silver.<br>Assessment Report 25158 |
| 1997                        | N | Assay/analysis<br>Grab |                  |                    |   |
| OUTCROP                     |   |                        | Copper           | 0.362 %            | Two grab samples (28345 and 38246) of carbonate, chlorite and hematite altered andesitic volcanics hosting malachite yielded 0.166 and 0.362 per cent copper, respectively.<br>Assessment Report 25158                  |
| 1997                        | N | Assay/analysis<br>Grab |                  |                    |   |
| OUTCROP                     |   |                        | Copper<br>Silver | 1.52 %<br>6.8 g/t  | A composite grab sample (28501) of andesite to basalt with quartz+/-carbonate stringers and malachite.<br>Assessment Report 24522   |
| 1996                        | N | Assay/analysis<br>Grab |                  |                    |   |
| OUTCROP                     |   |                        | Copper           | 0.34 %             | Chip sample (28502) of andesite to basalt with quartz+/-carbonate stringers and malachite over 4.5 metres.<br>Assessment Report 24522   |
| 1996                        | N | Assay/analysis<br>Chip |                  |                    |   |
| OUTCROP                     |   |                        | Copper           | 0.97 %             | A composite grab sample (28509) of silicified and malachite-stained andesite to basalt, taken to the northwest of the shaft.<br>Assessment Report 24522   |
| 1996                        | N | Assay/analysis<br>Grab |                  |                    |   |
| DUMP                        |   |                        | Copper           | 0.75 %             | A composite sample (28506) of dump material adjacent to the Portland shaft.<br>Assessment Report 24522  |
| 1996                        | N | Assay/analysis<br>Grab |                  |                    |   |
| DUMP                        |   |                        | Copper           | 0.4000 %           | Minister of Mines Annual Report 1913, page 223.   |
| 1913                        |   | Assay/analysis<br>Grab |                  |                    |   |
| OPENCUT                     |   |                        | Copper           | 0.9 %              | A sample from an open cut.<br>Minister of Mines Annual Report 1901, page 1183   |
| 1901                        | N | Assay/analysis<br>Rock |                  |                    |   |