

<b>MINFILE Number:</b> 092ISE132	<b>Name:</b> PEACOCK	<b>Status:</b> Showing
----------------------------------	----------------------	------------------------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
2015	N	Assay/analysis Grab	Copper	6.78 %	three float samples (P4, P5 and P7) from the Peacock occurrence area yielded from 2.71 to 6.78 per cent copper with 34 to 83 grams per tonne silver Assessment Report 35529
			Silver	83 g/t	
2012	N	Assay/analysis Grab	Silver	17.5 g/t	two samples (29 and 30) yielded greater than 1 per cent copper each with 9.3 and 17.5 grams per tonne silver and 0.377 and 0.633 gram per tonne gold, respectively. These samples were later re-sampled and yielded 1.33 and 2.31 per cent copper, respectively Assessment Report 33375 and 35529
			Gold	0.633 g/t	
2010	N	Assay/analysis Grab	Copper	2.31 %	a sample (no. 1) from the Clapperton Creek (Peacock) occurrence area Assessment Report 35529
			Gold	4.98 g/t	
1992	N	Assay/analysis Grab	Silver	287 g/t	sample 53063 Assessment Report 19933
			Copper	21.4 %	
1950	N	Assay/analysis Chip	Gold	1.03 g/t	In the 1940s or early 1950s, sampling of a trench is reported to have yielded 0.34 gram per tonne gold, 39.3 grams per tonne silver and 3.1 per cent copper over 13.5 metres Property File - 811079
			Silver	39.3 g/t	
			Copper	3.1 %	