

<b>MINFILE Number:</b> 093A 160	<b>Name:</b> LLOYD-NORDIK	<b>Status:</b> Developed Prospect
---------------------------------	---------------------------	-----------------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
UNDERGROUND 2012 N	Assay/analysis Drill Core	Copper Gold Silver	4.73 % 2.61 g/t 30.05 g/t	Over 12.8 metres (estimated true width of eight metres). Drillhole NDU12-196. PR REL Imperial Metals Corp. Jan. 7, 2013
UNDERGROUND 2011 N	Assay/analysis Drill Core	Copper Gold Silver	4.8 % 2.76 g/t 71.06 g/t	Over 35 metres. Drillhole NDU11-189. PR REL Imperial Metals Corp. Aug. 23, 2011
BOUNDARY 2009 N	Assay/analysis Drill Core	Copper	0.54 %	Over 7.5 metres. Drillhole ND09-96. EMPR ASS RPT 31472
LLOYD 2 1996 Y	7,190 kt Inferred	Gold Copper	0.2430 g/t 0.3100 %	Preliminary geological resource estimate for the Lloyd 2 target using a 0.10 per cent copper cutoff grade. At 0.25 per cent copper cutoff, the resource is 2,930,000 of 0.401 grams per tonne gold and 0.531 per cent copper. George Cross News Letter No.60 (March 25), 1996.
LLOYD 2 1996 Y	2,500 kt Indicated	Copper Gold	0.5500 % 0.3900 g/t	Cutoff grade of 0.20 per cent copper. Exploration in BC 1996, page C10.