

<b>MINFILE Number:</b> 093M 074	<b>Name:</b> GOLDEN WONDER (L. 3322)	<b>Status:</b> Showing
---------------------------------	--------------------------------------	------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE		Gold	1.91 g/t	
2019	N	Copper	0.41 %	Reeder, J.J. (2021-03-08): Technical Report on the Golden Wonder Property, South of New Hazelton, British Columbia, Canada
SAMPLE		Gold	20 g/t	
2017	Y	Silver	16.4 g/t	A chip sample (128288) of oxidized breccia with massive arsenopyrite veins. Reeder, J.J. (2019-05-21): Technical Report on the Golden Wonder Property
SAMPLE		Gold	18.7 g/t	
2017	N	Silver	100 g/t	A chip sample (128278) of oxidized mudstone with a 1.5-metre wide breccia zone hosting massive sulphides and quartz.
		Cobalt	0.653 %	Reeder, J.J. (2019-05-21): Technical Report on the Golden Wonder Property
		Copper	0.97 %	
SOUTHWEST		Gold	1.29 g/t	
2011	N	Silver	6.7 g/t	A 0.2-metre chip sample from a zone located approximately 450 metres to the south west of the main pit.
		Copper	0.234 %	Reeder, J.J. (2019-05-21): Technical Report on the Golden Wonder Property
MAIN		Gold	21.9 g/t	
2011	N	Silver	104 g/t	A rock sample from the main pit area.
		Copper	3.1 %	Reeder, J.J. (2019-05-21): Technical Report on the Golden Wonder Property
		Cobalt	1.21 %	
WEST		Copper	1.02 %	
2007	N	Gold	5.42 g/t	Chip sample (RD07-018) from a gravel pit located approximately 500 metres to the west.
		Cobalt	0.116 %	Burgoyne, A.A., Kikauka, A. (2007-12-18): Technical Report on the Rocher Deboule Property
MAIN		Gold	4.93 g/t	
2007	N	Silver	54.2 g/t	Chip sample (76051) over 0.6 metre.
		Copper	3.3 %	Burgoyne, A.A., Kikauka, A. (2007-12-18): Technical Report on the Rocher Deboule Property
		Cobalt	0.198 %	
MAIN		Silver	21.6000 g/t	
1980	N	Gold	5.5500 g/t	A 60-centimetre sample.
		Cobalt	0.1300 %	Assessment Report 8521.
		Copper	1.2100 %	