

<b>MINFILE Number:</b> 094E 017	<b>Name:</b> SAUNDERS	<b>Status:</b> Prospect
---------------------------------	-----------------------	-------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
A 2007	N Assay/analysis Grab	Gold Silver	0.04 g/t 33.6 g/t	A grab sample of 1 to 3 metre-wide crustiform quartz-pyrite veins. Assessment Report 30061
A 2007	N Assay/analysis Drill Core	Gold Silver	19.1 g/t 1020 g/t	Drill hole S-07-07 tested this mineralized outcropping, intersecting a mylonitic quartz-pyrite vein 42 metre vertically below the outcropping, that assayed 19.1 grams per tonne gold and 1020 grams per tonne silver over 0.3 metre. Assessment Report 30061
B 2004	N Assay/analysis Chip	Gold Silver	1.91 g/t 10.8 g/t	Chip sample (D208268) from the Saunders 'B' vein over 0.5 metre. Assessment Report 27760
A 2004	N Assay/analysis Chip	Gold Silver	23.05 g/t 590 g/t	Chip sample (D208253) from the Saunders 'A' vein over 3.0 metres. Assessment Report 27760
NORTHWEST 2004	N Assay/analysis Chip	Gold Silver	1.01 g/t 20.3 g/t	Sampling (no. 15) of the ridge to the north west of the Saunders occurrence. Assessment Report 27760
A 2003	N Assay/analysis Rock	Gold Silver	1.47 g/t 16.3 g/t	Sample 132634 from the Saunders 'A' vein. Assessment Report 27442
B 2003	N Assay/analysis Rock	Gold Silver	2.84 g/t 330.5 g/t	Sample 133560 from the Saunders B vein. Assessment Report 27442
B 1988	N Assay/analysis Grab	Silver	25.6 g/t	A sample (GWM-88-283) from the eastern 'B' vein. Assessment Report 18628
A 1988	N Assay/analysis Grab	Gold Silver	1.41 g/t 164.6 g/t	A sample (GWM-88-276) from the Saunders main vein assayed 1.41 grams per tonne gold and 164.6 grams per tonne silver, while three other samples (GWM-88-275, -277 and -280) from the main vein yielded from 0.02 to 0.40 gram per tonne gold and 16.5 to 34.0 grams per tonne silver. Assessment Report 18628

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
A		Gold	7.2 g/t	A sample (DD-S-23) from the Saunders main vein assayed 7.2 grams per tonne gold and 7.5 grams per tonne silver, while four other nearby samples (BT-S-16, -19, -20 and DD-S-26) yielded from 0.25 to 0.55 gram per tonne gold and 11.2 to 16.8 grams per tonne silver. Assessment Report 14487
1985	Assay/analysis Grab	Silver	7.5 g/t	
WEST		Gold	0.106 g/t	Two samples (DN-11 and -13) taken from zones of fracturing with strong silicification, epidotization and pyritization, located on the ridge to the west of the Saunders occurrence, yielded 0.104 and 0.106 gram per tonne gold with 0.4 and 7.6 grams per tonne silver, respectively. Assessment Report 10349
1981	Assay/analysis Grab	Silver	7.6 g/t	