

<b>MINFILE Number:</b>	094E 027	<b>Name:</b>	CASTLE MOUNTAIN	<b>Status:</b>	Showing
------------------------	----------	--------------	-----------------	----------------	---------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
SKARN			Silver	70.6 g/t	three samples (PD-84 to -86) from the main Castle massive galena-sphalerite skarn zone yielded values from 33.4 to 70.6 grams per tone silver, 0.253 to 1.802 per cent copper, 4.112 to 5.198 per cent lead and 6.408 to 18.410 per cent zinc  Property File - Delancy, P.R. [1989-10-01]: Final report on the 1989 exploration program Chappelle Property
1989	N	Assay/analysis	Copper	1.802 %	
		Grab	Lead	5.198 %	
			Zinc	18.410 %	
SOUTH			Gold	0.007 g/t	sample PD-106 of mineralized skarn, taken approximately 600 metres to the south of the main zone  Property File - Delancy, P.R. [1989-10-01]: Final report on the 1989 exploration program Chappelle Property
1989	N	Assay/analysis	Silver	5.1 g/t	
		Grab	Lead	0.298 %	
			Zinc	1.497 %	
WEST			Gold	0.443 g/t	sample PD-98 of mineralized skarn, taken approximately 400 metres west of the main zone  Property File - Delancy, P.R. [1989-10-01]: Final report on the 1989 exploration program Chappelle Property
1989	N	Assay/analysis	Silver	37.2 g/t	
		Grab	Lead	0.419 %	
			Zinc	4.198 %	
SKARN			Silver	10.6 g/t	a sample taken across 4.5 metres from the southern end of the main skarn zone  Property File – Crowhurst, J.J. [1973-06-25]: Report of the Castle Mountain Property of Oswood G. MacDonald to Macsan Explorations Ltd.
1973	N	Assay/analysis	Copper	0.20 %	
		Chip	Zinc	4.0 %	
SKARN			Lead	1.05 %	a sample (44706) of mineralized limestone (skarn?)  Property File - Cordilleran Exploration Corp. Ltd [1968-02-01]: Report - 1967-69 Toodoggone
1967	N	Assay/analysis	Zinc	12.0 %	
		Grab	Silver	390 g/t	
SKARN			Silver	47.9900 g/t	Assessment Report 14979.
1931	N	Assay/analysis	Copper	0.7900 %	
		Chip	Lead	3.9000 %	
			Zinc	32.5000 %	