

MINFILE Number:	094K 040	Name:	BOB 3-4	Status:	Prospect
------------------------	----------	--------------	---------	----------------	----------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
FLOAT			Copper	10.55 %	8 mineralized float samples from the EM-1 anomaly, located approximately 3 kilometres to the north-northeast, yielded from 0.71 to 10.55 per cent copper. Assessment Report 39913).
2021	N	Assay/analysis Grab			
VEIN			Copper	0.34 %	Chip sampling of the Neil vein in the Bob 3-4 occurrence area yielded an average of 0.34 per cent copper over a 20.1 metre section, while a bit further south another section averaged 0.87 per cent copper over 6.8 metres. Assessment Report 39913.
2021	N	Assay/analysis Chip			
SAMPLE			Copper	21.44 %	A sample of hematite breccia assayed 21.44 per cent copper and 9.5 grams per tonne silver, while a sample of mineralized shale yielded 0.94 per cent lead and 14.63 per cent zinc. Harrington, E. (2017-12-08): Technical Report on the Muskwa Property.
			Silver	9.5 g/t	
			Lead	0.94 %	
			Zinc	14.63 %	
2016	N	Assay/analysis Rock			
SAMPLE			Copper	15.47 %	Sample 5948 over 0.15 metre. Harrington, E. (2017-12-08): Technical Report on the Muskwa Property.
2011	N	Assay/analysis Chip			
FLOAT			Copper	24.0 %	Four float samples (B374246 through B374249) of quartz-carbonate vein material hosting massive to semi-massive chalcopyrite taken from a north-flowing creek, located approximately 4 kilometres north-northwest of the plotted location of the occurrence, yielded from 6.76 to 24.0 per cent copper. Assessment Report 28281.
2005	N	Assay/analysis Grab			
SAMPLE			Copper	0.246 %	A chip sample from the Neil vein over 1.0 metre. Assessment Report 27133.
2002	N	Assay/analysis Chip			
SAMPLE			Copper	9.95 %	Chip sampling of the Breccia zone, located near northeast mapped extent of the Neil vein, yielded 2.93 per cent copper over 13.9 metres, including 9.95 per cent copper over 1.0 metre. Harrington, E. (2017-12-08): Technical Report on the Muskwa Property; Assessment Report 24818.
1996	N	Assay/analysis Chip			
SAMPLE			Copper	3.6700 %	From Trench 2, in breccia zone, taken over 0.9 metre. Assessment Report 3420.
1971	N	Assay/analysis Chip			