

<b>MINFILE Number:</b> 104B 338	<b>Name:</b> KING	<b>Status:</b> Showing
---------------------------------	-------------------	------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
TRENCH 2015	Y Assay/analysis Chip	Silver Lead Zinc	294.7 g/t 6.04 % 13.35 %	Sample over a 6 metre thickness within the best mineralized section of Trench H. Assessment Report 35920
TRENCH 2015	Y Assay/analysis Chip	Silver Lead Zinc	98.6 g/t 0.85 % 3.55 %	Trench A sample over a 5 metre width. Assessment Report 35920
KING VEIN 1988	N Assay/analysis Chip	Silver Gold	122.0000 g/t 864.0000 g/t	20.0 centimetre chip sample taken across the King Vein and adjacent wallrock. Statement of Material Facts #66/88, Adrian Resources Ltd., Aug.5/88.
SAMPLE 1988	N Assay/analysis Chip	Gold	34.29 g/t	Chip samples indicate a weighted average grade of 34.29 gold over an average vein width of 0.30 metres. Assessment Report 18129.