

<b>MINFILE Number:</b> 104B 471	<b>Name:</b> QUINN ESKAY	<b>Status:</b> Showing
---------------------------------	--------------------------	------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE 2019	N Assay/analysis Chip	Gold Silver Copper Lead	15.35 g/t 2790 g/t 2.00 % 20 %	A 0.45 metre chip sample assayed 15.35 grams per tonne gold, 2790 grams per tonne silver, 2.00 per cent copper, 0.74 per cent zinc and greater than 20 per cent lead, while a 1.23 metre channel sample assayed 4.54 grams per tonne gold, 346.2 grams per tonne silver, 0.31 per cent copper and 5.87 per cent lead. Mitchell, A.J., Prowse, N.D. (2020-06-08): NI 43-101 Technical Report on the Doc Property.
SAMPLE 2011	N Assay/analysis Grab	Gold	0.83 g/t	Assessment Report 32600.
SAMPLE 1987	N Assay/analysis Grab	Gold Silver	0.79 g/t 277.7 g/t	A 'high-grade' grab sample assayed 1.89 grams per tonne gold and 647.4 grams per tonne silver, while the average of four grab samples yielded 0.79 gram per tonne gold and 277.7 grams per tonne silver. Mitchell, A.J., Prowse, N.D. (2020-06-08): NI 43-101 Technical Report on the Doc Property